Double Coated Tapes with Adhesive 300MP



9687 • 9690 • 9690B • 9690F • 9609 • 9693

Faceside¹

Adhesive

300MP/

0.0035"

(0.089mm)

300MP/

0.0015"

(0.038mm)

3M™ Double

Coated Tape

3M™ Double

Coated Tape

9609

9693

Technical Data June, 2007

Product Description

Construction

3MTM Double Coated Tapes with 3MTM Adhesive 300MP feature a thin polyester film for dimensional stability and improved handling with ease of die cutting and laminating. 3M adhesive 300MP offers excellent adhesion to many plastics and good shear strength and provides exceptional temperature and chemical resistance that withstands tough application environments. For information on storage and usage tips regarding the 3M adhesive 300MP products, please refer to technical bulletin, 3MTM Laminating Adhesives 300MP – Tips for storing, handling and slitting in roll form (70-0709-3905-6).

Backside¹

Adhesive

Liner

Tan, 83#,

Polycoated Kraft,

no print

Clear, PET,

no print

Total Tape

0.009"

(0.23mm)

0.0035"

(0.089mm)

0.0062"

(0.16mm)

0.002"

(0.051 mm)

Product Number	Type/ Thickness	Type/ Thickness	Type/ Thickness	Color, Type, Print	Liner Caliper	Thickness (w/o liner)
3M [™] Double Coated Tape 9687	300MP/ 0.0023" (0.058mm)	Clear PET ² 0.002" (0.051mm)	300MP/ 0.0077" (0.20mm)	Clear, PET, no print	0.002" (0.051mm)	0.012" (0.30mm)
3M [™] Double Coated Tape 9690	300MP/ 0.0028" (0.071mm)	Clear PET 0.0005" (0.013mm)	300MP/ 0.0023" (0.058mm)	Tan, 83#, Polycoated Kraft "3M"	0.0062" (0.16mm)	0.0055" (0.14mm)
3M [™] Double Coated Tape 9690B	300MP/ 0.0028" (0.071mm)	Black PET 0.0005" (0.013mm)	300MP/ 0.0023" (0.058mm)	Tan, 83#, Polycoated Kraft "3M"	0.0062" (0.16mm)	0.0055" (0.14mm)
3M™ Double Coated Tape 9690F	300MP/ 0.0028" (0.071mm)	Clear PET 0.0005" (0.013mm)	300MP/ 0.0023" (0.058mm)	Clear, PET, no print	0.002" (0.051mm)	0.0055" (0.14mm)
	(0.07 111111)	(0.01011111)	(0.00011111)			

Clear PET

0.002"

(0.051mm)

Clear PET

0.0005"

(0.013mm)

Carrier

Note 1: Faceside adhesive is on the interior of the roll.

The caliper listed is based on a calculation from manufacturing controlled adhesion coat weights using a density of 1.012 g/cc. While past data pages have listed a nominal caliper of 4.8 mils for 3M tapes 9690 and 9690B the coat weight has not changed.

300MP/

0.0035"

(0.089mm)

300MP/

0.0015"

(0.038mm)

Backside adhesive is on the exterior of the roll.

Note 2: PET (Polyester).

3M[™] **Double Coated Tapes with Adhesive 300MP** 9687 • 9690 • 9690B • 9690F • 9609 • 9693

Typical Physical Properties and Performance Characteristics	Note: The following technical information and data should be considered representative or typical only and should not be used for specification purposes.							
Product Number	3M™ Double Coated Tape 9687	3M™ Double Coated Tapes 9690, 9690B, 9690F	3M™ Double Coated Tape 9609	3M™ Double Coated Tape 9693				
Adhesion to stainless steel ASTM D3330 - 90 degree	Oz/in (N/100mm)	Oz/in (N/100mm)	Oz/in (N/100mm)	Oz/in (N/100mm)				
- 15 minute RT	50 (55)	45 (49)	74 (81)	37 (40)				
- 72 hour RT	53 (58)	116 (126)	87 (95)	61 (67)				
- 72 hour 158°F (70°C)	104 (114)	116 (126)	87 (95)	67 (73)				
ASTM D3330 - 180 degree, 2 mil Al fo	il							
- 72 hour RT	50 (55)	125 (136)	98 (107)	_				
ASTM D3330 - 180 degree, 2 mil polyester, stainless steel								
- 72 hour RT	_	_	_	70 (77)				
ASTM D3330 - 90 degree, 2 mil Al foil, 72 hour RT								
ABS	51 (56)	53 (58)	62 (68)	51 (56)				
Polyester	51 (56)	52 (57)	97 (106)	61 (67)				
Polycarbonate	62 (68)	52 (57)	100 (109)	_				
Shear Strength - ASTM D3654 modified - (.5 inch² sample size)								
1000 grams at 72°F (22°C)	4770 minutes	1500 minutes	1000 minutes	10,000 minutes				
500 grams at 158°F (70°C)	_	500 minutes	620 minutes	7076 minutes				
Less Bonding -		500N load cell with 15 age load (N) 106.2497						
Relative High Temperature Operating Ranges:								
Long Term (days, weeks)	200°F (93°C)	200°F (93°C)	200°F (93°C)	200°F (93°C)				
Short Term (minutes, hours)	300°F (149°C)	300°F (149°C)	300°F (149°C)	300°F (149°C)				
Available Sizes Roll length, width, slitting tolerance, con	re size.							
Available Lengths (Subject to minimum order requirements)								
Maximum Length								
1/2" to 63/64"		180 yd. (164 m)	_	180 yd. (164 m)				
3" to 48"		_	360 yd. (329 m)	_				
1" to 54"	360 yd. (329 m)	360 yd. (329 m)	_	360 yd. (329 m)				
Available Widths								
Minimum	4" (102 mm)	1/2" (12.7 mm)	3" (76.2 mm)	1/2" (12.7 mm)				
Maximum	54" (1372 mm)	54" (1372 mm)	48" (1220 mm)	54" (1372 mm)				
Normal Slitting Tolerance	±1/32" (0.8 mm)	±1/32" (0.8 mm)	±1/32" (0.8 mm)	±1/32" (0.8 mm)				
Core Size	6.0" (152.4 mm)	3.0" (76.2 mm)	6.0" (152.4 mm)	3.0" (76.2 mm)				

3M[™] Double Coated Tapes with Adhesive 300MP

9687 • 9690 • 9690B • 9690F • 9609 • 9693

Features

- 3MTM Double Coated Tape 9690B has a black film carrier which provides opacity and visibility.
- 3MTM Double Coated Tape 9690F is provided on a film liner for ease in rotary discutting and for applications that demand low particle generating parts.
- 3MTM Double Coated Tape 9609 provides easier handling and good gap filling for rigid to rigid substrate bonding.
- 3MTM Double Coated Tape 9693 clear polyester carrier provides dimensional stability and improved handling with ease of die cutting and lamination compared to adhesive transfer tapes.

Application Techniques

Bond strength is dependent upon the amount of adhesive-to-surface contact developed. Firm application pressure helps develop better adhesive contact and improves bond strength.

To obtain optimum adhesion, the bonding surfaces must be clean, dry and well unified. Some typical surface cleaning solvents are isopropyl alcohol or heptane.*

Ideal tape application temperature range is 70° F to 100° F (21° C to 38° C). Initial tape application to surfaces at temperatures below 50° F (10° C) is not recommended because the adhesive becomes too firm to adhere readily. However, once properly applied, low temperature holding is generally satisfactory.

*Carefully read and follow the manufacturer's precautions and directions for use when working with solvents. These cleaning recommendations may not be compliant with the rules of certain Air Quality Management Districts in California; consult applicable rules before use.

Application Ideas

- Cellular phone lens attachment
- Foam Lamination
- Nameplates
- Appliques
- Decorate Trim
- Thermal and sound dampening applications in the electronics and appliance industry.

Liner Configure Guide

General purpose steel rule die cutting 58# PCK (Polycoated Kraft)

Steel rule cutting many nameplates on common sheet

Kiss cutting, steel rule

Rotary die-cutting

83# PCK

83# PCK

PET

Selective die-cutting (cut adhesive before laminate)

Double-linered

Thermoforming HDPE (High density Polyethylene)

Part inspection HDPE, PET

Embossed metal parts White PP (polypropylene), HDPE

Metal parts (punch press) PET

Adding Liners to 3MTM Double Coated Tapes with 3MTM Adhesive 300MP

- 1. Rotary processing, tape only, on a densified (outside of #4994) kraft liner. In this process the tape waste will stay with the 83# PCK liner, leaving adhesive die-cuts dispensable from the #4994 (densified kraft) liner.
- 3MTM Adhesive 300MP 2. Rotary processing for finished parts. It is most efficient to use the polyester linered double coated 3M tape 9690F. Current process limitations prevent the supply of 3MTM Adhesive 300MP on a DK liner.

3M[™] Double Coated Tapes with Adhesive 300MP

9687 • 9690 • 9690B • 9690F • 9609 • 9693

Application Equipment

To apply adhesives in a wide web format, lamination equipment is required to ensure acceptable quality. To learn more about working with pressure-sensitive adhesives please refer to technical bulletin, *Lamination Techniques for Converters of Laminating Adhesives* (70-0704-1430-8).

For additional dispenser information, contact your local 3M sales representative, or the toll free 3M sales assistance number at 1-800-362-3550.

Storage

Store in original cartons at 70°F (21°C) and 50% relative humidity.

Shelf Life

If stored under proper conditions, product retains its performance and properties for two years from date of manufacture.

Certification/ Recognition

MSDS: 3M has not prepared a MSDS for these products which are not subject to the MSDS requirements of the Occupational Safety and Health Administration's Hazard Communication Standard, 29 C.F.R. 1910.1200(b)(6)(v). When used under reasonable conditions or in accordance with the 3M directions for use, the products should not present a health and safety hazard. However, use or processing of the products in a manner not in accordance with the directions for use may affect their performance and present potential health and safety hazards.

TSCA: These products are defined as articles under the Toxic Substances Control Act and therefore, are exempt from inventory listing requirements.

Product Use

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method of application.

Warranty and Limited Remedy

Unless stated otherwise in 3M's product literature, packaging inserts or product packaging for individual products, 3M warrants that each 3M product meets the applicable specifications at the time 3M ships the product. Individual products may have additional or different warranties as stated on product literature, package inserts or product packages. 3M MAKES NO OTHER WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY IMPLIED WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY ARISING OUT OF A COURSE OF DEALING, CUSTOM OR USAGE OF TRADE. User is responsible for determining whether the 3M product is fit for a particular purpose and suitable for user's application. If the 3M product is defective within the warranty period, your exclusive remedy and 3M's and seller's sole obligation will be, at 3M's option, to replace the product or refund the purchase price.

Limitation of Liability

Except where prohibited by law, 3M and seller will not be liable for any loss or damage arising from the 3M product, whether direct, indirect, special, incidental or consequential, regardless of the legal theory asserted, including warranty, contract, negligence or strict liability.



ISO 9001:2000

This Industrial Adhesives and Tapes Division product was manufactured under a 3M quality system registered to ISO 9001:2000 standards.

Industrial Business
Converters Markets
Industrial Adhesives and Tapes Division
2M Control Building 21 13W 10,000 Bush

3M Center, Building 21-1W-10, 900 Bush Avenue St. Paul, MN 55144-1000 800-223-7427 • 651-778-4244 (fax) www.3M.com/converter



Recycled Paper 40% pre-consumer 10% post-consumer

3M is a trademark of 3M Company. Printed in U.S.A. ©3M 2006 70-0709-3925-4 (6/07)