

EC-2000 SERIES CONDUCTIVE SILICONES

TYPICAL PROPERTIES	Test Method	EC-2040		EC-2130	
Filler		Nickel-Graphite			
Base Polymer		Silicone			
Specific Gravity, g/cc		2.18		1.97	
Thickness:					
inches		0.020 - 0.063		0.063 - 0.125	
mm		0.50 - 1.59		1.59 - 3.18	
Hardness:					
Shore A	ASTM D 2240	40		30	
Shore OO		85		80	
Tensile Strength, psi, min.	ASTM D 412	90		50	
Elongation, %, min.		60		50	
Compression Set @ 100°C, 25% compressed:	ASTM D 395 (Method B)				
% of thickness		6		7	
% of deflection		22		25	
Compression Set @ 70°C, 25% compressed	ASTM D 3574				
% of thickness		3		5	
% of deflection		12		17	
At Thickness indicated:	Horizontal	0.020	0.031	0.063	0.125
Flame Resistance, UL94*		HB	HB	HB	HB
		Vertical	V-1	V-1	*
Volume Resistivity, Ohm-cm (expression of conductivity)	Rogers Corporation Internal	0.2		0.3	
Shielding Effectiveness, dB:	At Thickness:	0.020"		0.063"	
100MHz	MIL G83528	120		100	
500MHz	MIL G83528	120		100	
1GHz	MIL G83528	110		110	
10GHz	MIL G83528	85		85	

* UL file No. E83967 reflects UL94 vertical and horizontal rating results.

The information contained in this data sheet is intended to assist you in designing with Rogers BISCO Silicones. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the data sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers BISCO Silicones for each application.