

## COHRLastic 3320 FIBERGLASS REINFORCED SOLID

### PRODUCT DESCRIPTION

COHRLastic® CF3320 is a thin flexible abrasion resistant reinforced general purpose silicone rubber. This product is often used as belting, gasketing and press pads. CF3320 offers an asbestos free gasketing that will function through a wide temperature range. **CF3320 HAS PROVEN SUCCESSFUL AS A GENERAL PURPOSE FLEX OPERATION PRESS PAD.**

### APPLICATION ADVANTAGES

- Unlimited life at room temperature
- Silicone is odorless, Dimensionally Stable
- Formulated to meet AMS 3320 Rev. G specification
- Good conformability, Lubricating oil resistant
- Excellent compression set resistance, smooth void free surface
- Balanced coating provides two working surfaces
- Approximate cycle life is 200

### PHYSICAL PROPERTIES \*

### TEST METHOD

Thickness	(inch)	.062, .093, .125	ASTM D-751
Fiberglass	(style)	1564	-----
Fiberglass Thickness	(inch)	.014	ASTM D-751
Break Strength, Warp	(ppi)	300	ASTM D-751
Elongation	( % )	<10	ASTM D-751
Diaphragm Burst Strength	(psi)	750	ASTM D-751
Weight by thickness	(lbs/yd <sup>2</sup> )	.062 = 4.1, .093 = 5.9, .125 = 7.8	ASTM D-575
Durometer with fabric	(shore A)	.062 = 74, .093 = 66, .125 = 65	ASTM D-2240
Durometer rubber comp.	"	50	ASTM D-2240
Weight loss, 4 hrs @ 400° F	(%)	1.0	-----
Temperature Range	(° F)	-100- +500	-----
Press Pad Temp. limit	(° F)	350	-----
Color		Red	-----

\*All physical properties are typical values and should not be used for writing specifications.

### AVAILABILITY

Factory stock is available as 36" wide yard goods.

*Important Notice To Purchaser: The following is made in lieu of all warranties, expressed or implied. Seller's and manufacturer's only obligation shall be to replace such quantity of the product found to be defective. Neither seller or manufacturer shall be liable for any injury, loss or damage, direct or con-sequential arising out of the use of or the inability to use the product. Before using, user shall determine the suitability of the product for his intended use, and the user assumes all risk and liability whatsoever in connection therewith. The foregoing may not be changed except by an agreement signed by officers of seller and manufacturer.*