




STOCKWELL ELASTOMERICS, INC.

4749 Tolbut Street Philadelphia, PA 19136
(800) 523-0123 (215) 335-3005 Fax (215) 335-9433
www.stockwell.com e-mail: service@stockwell.com



SNE-540

Compound: Conductive Silicone with Nickel-Graphite Filler

Property	Typical Values
Durometer, Shore "A"	40 (range: 35-45)
Volume Resistivity, ohm-cm	0.07
*Shielding Effectiveness, dB	80 (@ 20 MHz - 10 GHz)
Tensile Strength, psi	180
Elongation, max %	200
Tear "B", pli	40
Temperature Low, °C (°F)	-55 (-67)
Temperature High, °C (°F)	160 (320)
Specific Gravity	2.00
Color	Black
Mil-G-83528C	N/A
Available configurations	<ul style="list-style-type: none"> • Sheets (.020" - .062" thick) • Fabricated Gaskets • Molded Shapes

All values are typical and not intended for writing specifications.

* Additional data available upon request

4749 Tolbut Street, Philadelphia PA, 19136

P: 800-523-0123 (USA), 215-335-3005 | F: 215-335-9433 | E: service@stockwell.com

Copyright ©2007 Stockwell Elastomerics, Inc. All Rights Reserved