



BISCO® Silicones



BISCO® HT-870 Soft Cellular Silicone

Typical Product Properties

PROPERTY	TEST METHOD	VALUE
PHYSICAL		
Density, lb. / ft ³ (kg / m ³)	ASTM D 3574	15 (240)
Thickness, inches (mm)	---	1/16 to 1/2 (1.6 to 12.7)
Tolerance		See reverse
Standard Widths, inches (mm)		36 (914)
Standard Colors		Black, Red
Compression Force Deflection, psi (KPa)	Force Measured @ 25% Deflection ASTM D 1056	2-7 (14-48)
Compression Set, % max.	ASTM D 1056 Test D @ 158°F (70°C) ASTM D 1056 Test D @ 212°F (100°C)	<1 <5
Tensile Strength, Min. psi (kPa),	ASTM D 412	40 (276)
Tensile Elongation, % min.,	ASTM D 412	90
Environmental Properties		
Water Absorption	ASTM D 471	2.50 %
UV Resistance	SAE J - 1960	No Degradation
Ozone Effect Rating	ASTM D 1171	0 (No Cracks)
Stain Resistance	ASTM D 925(A)	No Staining
Corrosion Resistance	AMS - 3568	Pass
Flammability & Outgassing		
Flame Resistance	UL 94	Listed HF-1 & V-0
Flame Spread Index	ASTM E 162	<25
Limiting Oxygen Index	ASTM D 2863	38%
Smoke Density	ASTM E 662 Tested @ 4.0 minutes Tested @ 1.5 minutes	<50 <20
Toxic Gas Emissions Rating	SMP – 800-C & BSS 7239	Pass
Weight Loss	ASTM D 573 After 168 Hours @ 275°F (135°C)	1.05%

Please see reverse side for additional data.

HT-870 Soft Cellular Silicone (Continued)

PROPERTY	TEST METHOD	VALUE
Electrical & Thermal Properties		
Dielectric Constant	ASTM D 149	1.38
Dielectric Strength	ASTM D 150, Volts/mil	90
Dry Arc Resistance	ASTM D 495, Seconds	91
Volume Resistivity, Ohm – cm	ASTM D 257	10 ¹⁴
Thermal Conductivity, BTU in/hr/ft ² /°F (w/m °K)	ASTM C 518	0.49 (0.07)
Temperature Resistance		
Hot Flex	ASTM D 573 Tested @ 446°F (230°C)	Pass
Low Temperature Embrittlement, °F (°C)	ASTM D 746 (B) Tested @ -67 °F (-55°C)	Pass
Recommended Use Temperature, °F (°C)	SAE J-2236	-67- 392 (-55 – 200)
Recommended Intermittent High Temperature Use, °F (°C)	Internal	482 (250)

Standard Thickness Tolerance

Standard Thickness			Tolerance (Inches)
Inches		mm	
1/16	0.062	1.57	+/- 0.020
3/32	0.094	2.39	+/- 0.020
1/8	0.125	3.18	+/- 0.025
3/16	0.188	4.76	+/- 0.025
1/4	0.250	6.35	+/- 0.030
3/8	0.375	9.53	+/- 0.045
1/2	0.500	12.70	+/- 0.050

Width Tolerance (Cellular)

Nominal Width (Inches)	Tolerance without PSA	Tolerance with PSA
0 < T ≤ 3	+/- 0.063	+/- 0.031
3 < T ≤ 8	+/- 0.094	+/- 0.031
8 < T ≤ 12	+/- 0.125	+/- 0.031
12 < T ≤ 18	+/- 0.188	+/- 0.031
18 < T ≤ 26	+/- 0.219	+/- 0.063
26 < T ≤ 36	+/- 0.250	+/- 0.063

Notes:

1. All metric conversions are approximate.
2. Additional technical information is available.

The information contained in this data sheet is intended to assist you in designing with Rogers BISCO Silicones. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the data sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers BISCO Silicones for each application.