



Stockwell
ELASTOMERICS

TECHNICAL DATA SHEET

SNEF-60



SNEF-60 | 60 Durometer Conductive Fluorosilicone Rubber with Nickel / Graphite Filler

SNEF-60 is a fluorosilicone polymer with nickel-coated graphite particle fill, giving it very good shielding and grounding properties with added chemical resistance due to the fluoropolymer. High performance and competitively priced, SNEF-60 makes an excellent option for commercial and military EMI applications.

Stockwell Elastomerics offers pre-production and full production parts made from SNEF-60, including waterjet cutting, die cutting or molding. 3M conductive adhesive backing is also available for cut parts and select molded parts.

SNEF-60 Details

Property	Typical Value
Durometer, Shore "A", (+/- 5)	63
Volume Resistivity, ohm-cm	0.05
Shielding Effectiveness, dB	>100 (@20MHZ-10GHZ)
Tensile Strength, minimum, psi	200
Elongation, min %	200
Tear "B", min ppi	35
Temperature Low, °C (°F)	-55 (-67)
Temperature High, °C (°F)	200 (392)
Specific Gravity	2.20

*Additional data available upon request.

Additional Specifications

- Available Colors: Dark Grey
- Available Configurations: Sheets, Cut Parts (Waterjet, Die Cut), Conductive Adhesive Backed, Molded Parts
- MIL-DTL-83528 Not Applicable.

Scan To Learn More:



Stockwell Elastomerics, Inc.
4749 Tolbut St. Philadelphia, PA 19136-1512 USA
800.523.0123 | 215.335.3005

100% Employee Owned
AS9100 | ISO9001 Certified
www.stockwell.com | service@stockwell.com

