



EXPERTS IN SILICONE GASKET SOLUTIONS

→ [Click Here to Contact Us](#)

service@stockwell.com

215-335-3005



BISCO® HT-1200 Series

Product Data Sheet

BISCO® HT-1200 general purpose solid silicone series offers resistance to high temperatures, tear, and most fluids for a variety of industrial applications. Material is compliant with A-A-59588, AMS 3301-3304, and FDA 21 CFR 177.2600.

PROPERTY	TEST METHOD	STANDARD DUROMETER			
PHYSICAL		1240	1250	1260	1270
Color	Visual	Red (Stocked) Black, Gray, White (Made to Order)			
Thickness, mm (inches)	Internal	0.79 - 3.18 (0.031 - 0.125)			
Specific Gravity, (g/cc)	Internal	1.1	1.16	1.23	1.29
Durometer, Shore A	ASTM D2240	40 ± 5	50 ± 5	60 ± 5	70 ± 5
Compression Set, % max	ASTM D395 70 hrs @ 150°C (302°F)	25	25	25	25
Tensile Strength, kPa (psi)	ASTM D751	7650 (1110)	7100 (1030)	6950 (1010)	7200 (1050)
Tensile Elongation, %	ASTM D412	530	370	260	210
EFFECTS OF DRY HEAT AGING					
Change in Hardness, Shore A, max		±10	±10	±10	±10
Change in Tensile Strength, % max	ASTM D573 70 hrs @ 225°C (437°F)	-20	-20	-20	-25
Change in Elongation, % max		-40	-40	-40	-40
EFFECTS OF WATER IMMERSION					
Change in Volume, %	ASTM D471 70 hrs @ 100°C (212°F)	+10	+5	+5	+5



The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers BISCO products for each application. The Rogers logo, BISCO logo, and BISCO are trademarks of Rogers Corporation or one of its subsidiaries. © 2003, 2019 Rogers Corporation. All rights reserved. 1019-PDF • Publication #180-068

PROPERTY	TEST METHOD	STANDARD DUROMETER			
THERMAL PROPERTIES		1240	1250	1260	1270
Low Temperature Brittleness, °C (°F)	ASTM D2137 -62.2 (-80)	Pass	Pass	Pass	Pass
Recommended Use Temperature, °C (°F)	Internal	-62 to 218 (-80 to 425)			

Standard Thickness Tolerances

NOMINAL THICKNESS	TOLERANCE
mm (inches)	mm (inches)
0.7874 (0.031)	± 0.127 (± 0.005)
1.6002 (0.063)	± 0.1651 (± 0.0065)
2.3876 (0.094)	± 0.254 (± 0.010)
3.175 (0.125)	± 0.4318 (± 0.017)

Slit Material and Tape (PSA) Width Tolerances

NOMINAL WIDTH	TOLERANCE
mm (inches)	mm (inches)
> 0 - 76 (> 0 - 3)	± 1.60 (± 0.063)
> 76 - 203 (> 3 - 8)	± 2.39 (± 0.094)
> 203 - 305 (> 8 - 12)	± 3.18 (± 0.125)
> 305 - 610 (> 12 - 24)	± 4.78 (± 0.188)
> 610 - 914 (> 24 - 36)	+ 25.4/- 0 (+ 1/- 0)

VALUE ADDED OFFERINGS

- Adhesive (PSA) lamination
- Slit material/tapes

Notes:

- All metric conversions are approximate. Reference US customary units for official values and tolerances.
- Additional technical information is available.
- Values should not be used for specification limits.