



**STOCKWELL
ELASTOMERICS**
MANUFACTURING SOLUTIONS
THROUGH ENGINEERED MATERIALS

➔ [click here to contact us](#)
e-mail: service@stockwell.com • (800) 523-0123

High Performance Foams Division
171 West St. Charles Road
Carol Stream, IL 60188
Tel: 630.784.6200 / Fax: 630.784.6201
www.rogerscorporation.com

Typical Product Properties

BISCO® HT-1500 (AMS-3320) Fiberglass Reinforced Silicone Sheet

PHYSICAL PROPERTY		TYPICAL VALUE	
Durometer, Shore "A" (pts)		70 +/-10	
Tensile Strength – Warp (ppi)		300 min.	
Tensile Strength – Fill (ppi)		300 min.	
STANDARD PRODUCT THICKNESS		TOLERANCE	RANGE
1/32" *	0.031" *	+/- 0.006"	0.025" – 0.037"
1/62"	0.0625"	+/- 0.0095"	0.053" – 0.072"
3/32"	0.094"	+/- 0.015"	0.079" – 0.109"
1/8"	0.125"	+/- 0.015"	0.110" – 0.140"

*Note: 1/32" is not AMS 3320 certified

WIDTH TOLERANCE	
NOMINAL WIDTH	TOLERANCE (+/-)
0" – 12"	0.125"
>12" – 18"	0.1875"
>18" – 24"	0.1875"
>24" – 30"	0.250"
>30" – 36"	0.250"

The information contained in this data sheet is intended to assist you in designing with Rogers BISCO Silicones. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown on the data sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers BISCO Silicones for each application.

The world runs better with Rogers.®

BISCO is a licensed trademark of Rogers Corporation.
© 2003 Rogers Corporation, Printed in U.S.A. All rights reserved.
3085-1003-0.4C, **Publication #180-077**