



EXPERTS IN SILICONE GASKET SOLUTIONS

→ [Click Here to Contact Us](#)

service@stockwell.com

215-335-3005

BISCO® HT-820 Firm Silicone Foam



BISCO® HT-820 firm silicone foam exhibits enhanced sealing capabilities comparable to sponge rubber. It's designed for use in enclosures requiring a durable, high closure force gasket. Patented chemistry and cell structure provide a long-term performance advantage.

Features & Benefits:

- Enhanced durability and sealing performance
- High tear and tensile strength comparable to a traditional sponge rubber
- Resistance to UV, ozone, and extreme temperatures for consistent performance across many environments
- Rated to most stringent UL flame standards

PROPERTY	TEST METHOD	TYPICAL VALUE*	SPECIFICATION**
PHYSICAL			
Color	Visual	Gray	---
Thickness, mm (inches)	Internal	0.79 - 6.35 (0.031 - 0.250)	See "Width Tolerance" table
Density, kg/m ³ (lb./ft ³)	Internal	384 (22)	336 - 528 (21 - 33)
Compression Force Deflection, kPa (psi)	ASTM D1056	106 (15.3)	82 - 138 (12 - 20)
Compression Set, %	ASTM D1056 100°C (212°F) / 22 hrs / 50%	2.6	< 5
Water Absorption, %	Internal 2" below water surface / 24 hrs / change in weight	0.5	< 5
FLAMMABILITY			
Flame Resistance	UL 94 (File E83967)	Meets	V-0
Flame Spread Index (Is)	ASTM E162	Meets	Flaming Mode < 35
Smoke Density (Ds)	ASTM E662	Meets	Flaming Mode, 1.5 min, < 100 Flaming Mode, 4.0 min, < 200
Burn Length	FMVSS 302	Meets	< 100 mm/min
THERMAL			
Temperature Range, °C (°F)	Internal	-55 to +200 (-67 to +392)	---
Thermal Conductivity, W/m °K	ASTM C518	0.09	---
Low Temperature Flex	ASTM D1056 -55°C (-67°F) / 5 hrs	Pass	---
Low Temperature Brittleness	ASTM D746 -55°C (-67°F) / 3 min	Pass	---

Specification values in bold are tested on a batch basis.



The information contained in this Data Sheet is intended to assist you in designing with Rogers' Elastomeric Material Solutions. It is not intended to and does not create any warranties, express or implied, including any warranty of merchantability or fitness for a particular purpose or that the results shown in this Data Sheet will be achieved by a user for a particular purpose. The user should determine the suitability of Rogers BISCO products for each application. The Rogers logo, BISCO, and the BISCO logo are trademarks of Rogers Corporation or one of its subsidiaries. © 2003, 2006, 2007, 2009, 2017, 2019, 2020, 2022, 2023 Rogers Corporation. All rights reserved. 1223-PDF • Publication #180-071 www.rogerscorp.com

PROPERTY	TEST METHOD	TYPICAL VALUE*	SPECIFICATION**
OUTGASSING			
Total Mass Loss (%)	ASTM E595 (4x10 ⁻⁶ Torr)	2.11	---
Collected Volatile Condensable Materials (CVCM) (%)	ASTM E595 (4x10 ⁻⁶ Torr)	0.63	---
Water Vapor Regain (%)	ASTM E595 (4x10 ⁻⁶ Torr)	0.02	---
ELECTRIC			
Dielectric Strength, Volts/mil	ASTM D149	66	---
Dielectric Constant, 1 kHz	ASTM D150	1.7	---
Dissipation Factor, 1 kHz	ASTM D495	0.006	---
Dry Arc Resistance, Seconds	ASTM D495	174	---
Volume Resistivity, Ohm-cm	ASTM D257	10 ¹⁴	---

Standard Thickness Tolerances

NOMINAL THICKNESS	TOLERANCE
mm (inches)	mm (inches)
0.79 (0.031)	± 0.381 (± 0.015)
1.59 (0.063)	± 0.508 (± 0.020)
2.39 (0.094)	± 0.508 (± 0.020)
3.18 (0.125)	± 0.635 (± 0.025)
4.78 (0.188)	± 0.635 (± 0.025)
6.35 (0.250)	± 0.762 (± 0.030)

Slit Material and Tape (PSA) Width Tolerances

NOMINAL WIDTH	TOLERANCE
mm (inches)	mm (inches)
> 0 - 76 (> 0 - 3)	± 1.60 (± 0.063)
> 76 - 203 (> 3 - 8)	± 2.39 (± 0.094)
> 203 - 305 (> 8 - 12)	± 3.18 (± 0.125)
> 305 - 457 (> 12 - 18)	± 4.78 (± 0.188)
> 457 - 660 (> 18 - 26)	± 5.56 (± 0.219)
> 660 - 914 (> 26 - 36)	+ 25.4/- 0 (+ 1/- 0)

VALUE ADDED OFFERINGS

- Adhesive (PSA) lamination
- Slit material/tapes

SPECIFICATION

- AMS3196

Notes:

*Typical Value- Value is based on historical data. Please note the frequency of testing varies.

**Specification- Applies to physical properties only, which are based on Rogers' internal benchmark and standard BISCO specification values. Additional industry specifications are available as well. All other properties are based on industry standard guidelines.