



NORSEAL®

3320, 4032 & 4050

Providing protection in your environment



**STOCKWELL
ELASTOMERICS**

MANUFACTURING SOLUTIONS
THROUGH ENGINEERED MATERIALS

[click here to contact us](#)

e-mail: service@stockwell.com • (800) 523-0123

Reinforced Solid Silicone Rubber

Saint-Gobain NORSEAL® reinforced solid silicone with fiberglass is a dimensionally stable, durable material for press pads, belting and gasketing. 3320 was developed to meet AMS 3320 standards and features lubricating oil resistance and excellent compression set resistance. 4032 and 4050 are thin, flexible and abrasion resistant for general purpose use and expansion joints.

NORSEAL reinforced solid silicone products are specially designed to provide the following features:

- Balanced coating provides two working surfaces
- Smooth, defect-free surface
- Low compression set
- Low outgassing
- Dimensionally stable
- Long cycle life in press pad applications
- Conformable

Available Sizes

Standard thickness: see roll size chart on following page

Master roll size: 36 in. (914 mm) x continuous lengths

Special thickness and roll sizes also available.

Applications

- Flexible circuit boards
- Printed circuit boards
- Conveyor belts
- Expansion joint construction
- High pressure gaskets
- Duct work clamps



SAINT-GOBAIN

NORSEAL® 3320, 4032 & 4050 – Properties

(COHRLastic® 3320, 4032 & 4050)

Performance tests are run using standard test procedures. The values presented are typical values and should not be used for specification purposes.

Property	Test Method	3320	4032	4050
Durometer with Fabric	ASTM D2240	.062 = 74 .093 = 66 .125 = 65	81	75
Durometer with Rubber Compound	ASTM D2240	50	50	50
Elongation: %	ASTM D751	<10	<10	<10
Tensile Strength Wrap: ppi	ASTM D751	300	300	300
Fiberglass Thickness: in.	ASTM D751	.014	.014	.014
Weight Loss, 4 hours @400°F: %	ASTM D573	1.5	1	1.5
Temperature Range: °F	—	-100 – +500	-100 – +500	-100 – +500
Color	—	Red	Gray	Gray

NORSEAL® 3320, 4032 & 4050 –Standard Roll Sizes

Product No.	Thickness in. (mm)
3320	.063, .094, .125 (1.59, 2.38, 3.18)
4032	.031 (.79)
4050	.05 (1.27)

Roll width: 36 in. x continuous length

Options (subject to minimum order requirements)

Talc-free interleaf liner for ease in winding.

Acrylic (or silicone) pressure-sensitive adhesive (PSA) available in sheet format only (see NORSEAL Silicone Elastomer Adhesive Option data page for details).

Important Instructions

- Because Saint-Gobain cannot anticipate or control every potential application, we strongly recommend testing of this product under individual application conditions prior to commercial use.
- When using PSA option, surfaces must be clean and free of oil, grease, moisture, dust and dirt. Isopropyl alcohol is good for cleaning the surface. Do not remove liner until tape is in proper position. Avoid touching adhesive surface before application.
- Recommended service temperature of the silicone elastomer is -100°F to 500°F (-73°C to 260°C).

Shelf Life

10 years after the date of sale for base material when stored in original packaging at temperatures up to 70°F (21°C) and 50% relative humidity (for optional PSA, see other data sheets).

NORSEAL® and COHRLastic® are registered trademarks of Saint-Gobain Performance Plastics.



Saint-Gobain Performance Plastics

14 McCaffrey St.
Hoosick Falls, NY 12090

Tel: (518) 686-7301
Fax: (518) 686-4840

foams@saint-gobain.com
www.foams.saint-gobain.com

The data and details in this document were correct and up-to-date at the time of printing and are intended to provide information on our products and their possible applications. It is the user's responsibility to obtain the latest version of the product data sheet. This data sheet is not a specification and does not assure specific product characteristics or make reference to the suitability of the product for a specific application. Because Saint-Gobain cannot anticipate or control every application, we strongly recommend testing of this product under individual application conditions. The application, use and conversion of this product are the user's responsibility.

Limited Warranty: For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse, or inability to use this product(s). SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

NOTE: Saint-Gobain Performance Plastics Corporation does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.