



PRESS MOLDED BUNS
PHYSICAL PROPERTIES

Table with 2 columns: Property and Value. Properties include Type (R-411-N), Polymer (Neoprene (CR)), Color (Black), ASTM D-1056-67 Classification (SCE-41), ASTM D-1056-00 Classification (2C1), UL 50 / 508 (JMST2 File #MH9949), 25% Compression Resistance (2 - 5), 50% Compression Set (25), Density (10 - 16), Water Absorption (0.1 max.), Tensile (50 min.), Elongation (150 min.), Flammability (Pass), Standard Sheet Size (42" x 56"), and Expected Yield (2.25").

- 1) 25% Compression Resistance ASTM D-1056
2) 50% Compression Set ASTM D-1056
3) Density ASTM D-1056
4) Water Absorption ASTM D-1667
5) Tensile ASTM D-412
6) Elongation ASTM D-412
7) Flammability - This item and any corresponding data refer to typical performance in the specific test indicated and should not be construed to imply this material's behavior in other fire conditions. UL 94-test valid for specific rating and thickness only. See UL 94 listing for details. (File # E55475).

Other gauges and widths may be available. Please refer to Customer Service

Note: SAEJ 18 is equivalent to ASTM D-1056

Issued 10/01/04