



# ELASTOSIL® LR 3003/40 A/B US

Liquid Silicone Rubber



# **Applications**

ELASTOSIL® LR 3003 A/B US Liquid Silicone Rubbers are paste-like, easily pigmentable, two-component liquid silicone rubbers with short curing times.

These grades are particularly suitable for the large scale, automated production of molded parts.

## **Key Characteristics**

- · Excellent catalyzed pot life
- Good mechanical strength
- High transparency
- Fast cure

## **Properties**

Typical Property values are not intended for use in the preparation of specifications. Please contact Wacker Silicones Division for assistance and recommendations before writing specifications on this product.

## **Processing**

ELASTOSIL® LR 3003/40 A/B US can be fabricated using standard liquid rubber injection molding techniques. The product is delivered equal parts A/B and designed for a 1:1 (A;B) mix ratio. With proper Imetering equipment, it can be pumped directly through a statixc mixer into the injection molding machine.

# **Product Data**

Property*	Test Procedure	Value
Appearance	WSTM 1279	Translucent
Specific Gravity, 25°C	WSTM 1154	1.14
Viscosity A/B, mPa-s	WSTM 3277	680,000/660,000
Pot Life, hrs, 25°C***	WSTM 2299	48
Hardness, Shore A	WSTM 1110	40
Tensile Strength	WSTM 1160	
MPa		9.8
psi		1380
Elongation, %	WSTM 1160	620
Tear Strength, die B	WSTM 1160	
kN/m		30.5
ppi		175
Brittle Point, °C	ASTM D746	-73

<sup>\*</sup> Properties obtained after mixing Part A and Part B in a ratio of 1:1; press cured 5 min/166°C. Post cured 4 hrs/200°C \*\*\* Pot life determined by time required for extrusion rate to be reduced to 50% of initial value.

Version 5.00 / 19-05-11 / nr Page 1 / 2





It is best practice to postcure molded parts prior to use in food contact applications

### Storage

ELASTOSIL® LR 3003/40 A/B US has a shelf life of at least 12 months when stored below 32°C in the tightly closed original container. Storage beyond the recommended shelf-life does not necessarily mean that the product is no longer usable. However, the properties required for the intended use must be checked for quality assurance reasons.

Once opened, containers should always be resealed to prevent catalyst poisoning by amines, sulfur compounds, and other substances

## Safety

For detailed safety information, please refer to the Safety Data Sheet (SDS).

### **Packaging**

ELASTOSIL® LR 3003/40 A/B US Liquid Silicone Rubber is available in 36 kg. (80 lb.) pail kits and 364 kg. (800 lb.) drum kits.

#### **Contact Information**

Phone: 1800-554-1715 Press 1 for Silicone Rubber -Follow the menu instructions

e-mail: customercare@wacker.com

Wacker Silicones Wacker Chemical Corporation 3301 Sutton Road Adrian, Michigan 49221-9397

Wacker Silicones Division is a domestic manufacturer of basic silicone materials for industry. Products include silicone fluids and emulsions, antifoam and release agents, room temperature vulcanizing (RTV) sealants and adhesives, heat curable rubber (HCR), liquid silicone rubber (LSR), masonry water repellents, paint raw materials, paper release coatings, and textile finishes

Because we cannot foresee the varied conditions under which this information and our materials may be used, we do not guarantee the applicability or accuracy of this information or the suitability of our materials in any specific situation. Samples are provided and users should make their own tests to determine the suitability of our materials for their specific purposes. These materials are provided without warranty, either expressed or implied, of fitness for a specific purpose and nothing herein shall be construed as a recommendation for uses, which infringe valid patents, or as extending a license under valid patents.

The management system has been certified according to ANSI/ISO/ASQ Q9001 And ANSI/ISO 14001



and ELASTOSIL® are registered trademarks of Wacker-Chemie AG. WACKER SILICONES Wacker Chemical Corporation 3301 Sutton Road Adrian, MI 49221 TEL: + 1 517 264 8500 FAX: + 1 517 264 8246 e-mail: customercare@wacker.com

www.wacker.com