#### **Product: EMI Gasket Materials**



#### Related Web Page:

https://www.stockwell.com/emi-gaskets/

#### Stockwell Value Proposition:

### **Design & Engineering**

Staff engineers comprehend design challenges and are available to help select materials and manufacturing processes that best fit specific application needs.

#### **Material Solutions**

Stockwell Elastomerics has strategically partnered with industry leaders such as Rogers Corp., Saint-Gobain, 3M, Wacker Silicones and Momentive Silicones to ensure the <u>highest quality materials</u> are used. Stockwell Elastomerics has a comprehensive inventory of engineered materials designed and manufactured to meet requirements of the most demanding gasketing applications.

Pre-Production through Manufacturing
Combining in-house CNC die cutting,
waterjet cutting, injection molding,
compression molding and adhesive
lamination with comprehensive inventory,
Stockwell Elastomerics can fulfill fast-turn
prototyping, pre-production and full
production requirements.

# **SNE-553**

Compound: 30 Durometer Conductive Silicone Rubber with Nickel / Graphite Filler

## **Product Description:**

SNE-553 is a soft silicone polymer with nickel coated graphite particle fill, giving it very good shielding and grounding properties. High performance and competitively priced, SNE-553 makes an excellent option for commercial and military EMI applications.

Stockwell Elastomerics offers pre-production and full production parts made from SNE-553, including waterjet cutting, die cutting or molding. 3M conductive adhesive backing is also available for cut parts and select molded parts.

Property	Typical Value
Durometer, Shore "A", (+/- 5)	30
Volume Resistivity, ohm-cm	0.125
Tensile Strength, minimum, psi	100
Elongation, min %	400
Temperature Low, °C (°F)	-60 (-76)
Temperature High, °C (°F)	200 (392)
Specific Gravity	1.70
Color	Black
Mil-G-83528	N/A
Available Configurations	Sheets     Cut Parts (Waterjet/Die Cut)     Molded Parts     Conductive Adhesive Backed

Email: service@stockwell.com 4749 TOLBUT STREET. PHILADELPHIA. PA. Website: www.stockwell.com 215-335-3005 / 215-335-9433 (FAX)